

# Byggcement

CEM II/A-LL 42,5 R



## CEMENT TYPE AND CEMENT CLASS

Byggcement is a CEM II Portland-limestone cement manufactured in Skövde. It has normal compressive strength development and is used in standard concrete work, e.g. in house building. Technical data is on page 2 of this technical data sheet.

## STANDARDS AND CONTROL

Byggcement satisfies the requirements of SS-EN 197-1 Cement-Part 1: Composition, specifications and conformity criteria for common cements.

Byggcement Skövde is P-marked with certificate number 10 13 14 and CE-marked with certificate number 10 13 24.

## PACKAGING, DISTRIBUTION AND STORAGE

Delivery takes place in bulk, in 1,000 kg big bags or in 25 kg bags by Saint-Gobain Byggprodukter AB. Delivery terminals are listed in our price list. Storage in an environment that has an element of moist air or direct contact with ground moisture or water damages the cement very quickly (days, weeks).

Byggcement must be stored in a dry, sealed silo for a maximum of six months after delivery, as the chromate reduction process gradually loses its effect.

Cement in bags must be stored on plastic-coated storage pallets for a maximum of six months after the packing date. It is always the buyer's responsibility to make sure and be able to show that the storage location is dry and sealed, and that the storage time is observed.

## GENERAL TERMS OF DELIVERY

The delivery of Byggcement is subject to ABM 92 and Cementa's Special Terms and Conditions.

## SAFETY DURING HANDLING

All cement must be stored out of the reach of children and is dangerous to consume. Cement in the eyes creates a risk of serious eye damage. Moist cement forms calcium hydroxide, which irritates the skin and the respiratory organs. For complete information and instructions on protection, see the Material Safety Data Sheet.

## Product information

For the latest updates to the Technical Data Sheet and Material Safety Data Sheet, see our website [www.cementa.se](http://www.cementa.se).

# Technical data

Byggcement CEM II/A-LL 42,5 R

Byggcement Skövde and Slite complies with the data below.  
On rare occasions the values may deviate from the specified ranges or limits.

## PHYSICAL DATA

Property	Guideline value Skövde	Range	Unit	Requirement	Current standard
Blaine fineness	430	± 30	m²/kg		
Setting time	140	± 30	min	≥ 60	EN 197-1
Compressive Strength 1 d*	23	± 3	MPa		
Compressive Strength 2 d*	35	± 3	MPa	≥ 30	EN 197-1
Compressive Strength 7 d*		± 4	MPa		
Compressive Strength 28 d*	55	± 4	MPa	≥ 52.5	EN 197-1
Compact density	3 080	± 20	kg/m³		
Bulk density	1 250	± 250	kg/m³		
Brightness	26	± 1	%		

\*Measured on standard mortar

## CHEMICAL DATA

Property	Limits Skövde	Unite	Requirement	Current standard
Magnesium oxide, MgO	1.1-1.3	%	≤ 5.0	EN 197-1
Sulfates, SO <sub>3</sub>	3.3-4.0	%	≤ 4.0	EN 197-1
Chloride, C1 <sup>-</sup>	0.02-0.04	%	≤ 0.10	EN 197-1
Water-soluble, Cr <sup>6+</sup>	0-2	ppm	≤ 2 (In accordance with EG 2003/53 and KIFS 2004:6)	

## CEMENTA AB

P.O. Box 47210  
SE - 100 74 Stockholm  
Tel. +49 (0)8-625 68 00  
Fax +49 (0)8-753 36 20  
E-mail info@cementa.se  
Website www.cementa.se