

evoZero Industrisement Brevik

evoBuild CC Industrisement Brevik

CEM II/A-L 42,5 R

Industrisement Brevik is a Portland-limestone cement produced by Heidelberg Materials in Brevik, Norway.

The product fulfills the technical data below. On rare occasions the values may deviate from the specified ranges or limits.

Property		Value	Range	Requirements in EN 197-1
Compact density (kg/m ³)		3100	-	-
Setting time (min)		110	-	≥ 60
Specific surface (blaine, m ² /kg)		550	-	-
Brightness (%)		-	-	-
Compressive strength (MPa)	1 day	31	-	-
	2 days	39	-	≥20
	28 days	55	-	≥42.5 ≤62.5
Sulfates, SO ₃ (%)		≤4.0	-	≤ 4.0
Alkali, Na ₂ O _{eq} (%)		1.3	-	-
Chlorides, Cl ⁻ (%)		≤0.085	-	≤ 0.10
Water-soluble chromium Cr ⁶⁺ (PPM)		≤2	-	≤ 2 ¹
Clinker (%)		90	-	80-94
Limestone (%)		10	-	6-20

¹ Clause 47 of Annex XVII the REACH Regulation.

The maximum storage period is 6 months from the date of packaging for unbroken big bags and 6 months from the date of delivery for silos (bulk).

For further information and handling of cement, see the safety data sheet.